

# SHOUMAN



## PE Geomembrane 150 micron

Property	Test Method	Unit	Value
<b>Thickness</b>			
minimum average	ASTM D 5199	mm	0.150
Lowest Individual		%	- 10
<b>Density</b> (min. avg.)	ASTM D 1505	g/cm <sup>3</sup>	0.935- 0.940
<b>Tensile Properties</b>			
Strength at Yield	ASTM D - 6693	N/mm <sup>2</sup>	5
Elongation at Yield		%	8
Strength at Break		N/mm <sup>2</sup>	22
∅Elongation at Break		%	500
<b>Tear Resistance</b> (min. avg.)	ASTM D 1004	N	20
<b>Puncture Resistance</b> (min. avg.)	ASTM D 4833	N	30
<b>Stress Crack Resistance</b>	ASTM D 5397	hrs.	400
<b>Carbon Black Content</b>	ASTM D 4218	%	2.0 - 3.0
<b>Oxidation Induction Time</b> (OIT-Standard)	ASTM D 3895	Min.	100
<b>Dimensional Stability</b>	ASTM D 1204	%	± 2
<b>UV Resistance -</b> <i>% retained after 1600 hours</i>	GRI-GM 11		

### Note:

The above information obtained from analysis performed in our labs and was based on reliable and standard laboratory testing procedures. The information contained herein is to be used only as guide for using our film. SHOUMAN does not offer any guarantee on the results and does not accept any liability arising out of the use of the information contained herein.

[www.shouman.com](http://www.shouman.com)

8 El Gaish Street  
Mansoura - Egypt

info@shouman.com  
www.shouman.com

+2 . 050 . 2 . 300 . 200  
+2 . 050 . 2 . 300 . 600

