

Technical Data Sheet

Low Density Poly-Ethylene for General Purpose applications

Property	Value	Unit
Tensile Strength at Yield in MD	8	MPa
Tensile Strength at Yield in TD	7	MPa
Tensile Strength at Break in MD	21	MPa
Tensile Strength at Break in TD	18	MPa
Elongation at Break in MD	290	%
Elongation at Break in TD	570	%

Note:

The above values are measured for 20 μ film

www.shouman.com



8 El Gaish Street
Mansoura - Egypt



info@shouman.com
www.shouman.com



+2 . 050 . 2 . 300 . 200
+2 . 050 . 2 . 300 . 600