

Technical Data Sheet

Poly-Ethylene for Shrink applications

Property	Value	Unit
Tensile Strength at Yield in MD	11.8	MPa
Tensile Strength at Yield in TD	12.2	MPa
Tensile Strength at Break in MD	21.6	MPa
Tensile Strength at Break in TD	16.9	MPa
Elongation at Break in MD	370	%
Elongation at Break in TD	560	%

Note:

The above values are measured for 50 μ film

www.shouman.com



8 El Gaish Street
Mansoura - Egypt



info@shouman.com
www.shouman.com



+2 . 050 . 2 . 300 . 200
+2 . 050 . 2 . 300 . 600